



NEBAR BROWN

MATERIAL SPECIFICATION SHEET

Description

General Purpose High Quality Jointing. Nitrile/SBR bonded cork for < 3mm thickness, Polychloroprene/Nitrile bonded cork for >= 3mm thickness.

Specification Compliance

ASEA 1169 5012E – 204

ASTM F104 line call out - below 3 mm F224000M2, 3 mm and above F225000M2

Typical Properties

Material tested to procedures as documented in ASTM F104

	< 3 mm thick	≥ 3 mm thick	Test Procedure
Base elastomer	NITRILE/SBR	CR/NITRILE	
Thickness	0.8 to 2.5	3 to 13	
Hardness	65 to 85°	65 to 80°	ASTM D1415
Minimum tensile strength (MPa)	1.75	1.75	ASTM F152
Low temperature flexibility	-20°C	-30°C	
Maximum operating temperature in fluids	110°C	110°C	
Compressibility at 2.8 N/mm ²	15 to 25%	20 to 30%	ASTM F36
Recovery minimum	75%	75%	ASTM F36
Normal sheet size	1.2 x 1.0 1.2 x 1.2	1.2 x 1.2	
Flexibility	3d	3d	ASTM F147



ISO 9001:2015 Q93057 ISO 14001:2015 EMS 505718

The company's products are used for a multiplicity of purposes and as the company has no control over the method of their applications or use, the company excludes all conditions or warranties, expressed or implied by statute or otherwise, as to their products and/or their fitness for any particular purpose. Any technical co-operation between the company and the customer is given for customers assistance only and without liability on the part of the company

Fluid resistance, volume swells	< 3 mm thick	≥ 3 mm thick	Test Procedure
ASTM 1 72 hours at 100°C	-3 to +10%	0 to +10%	ASTM F146
IRM903 72 hours at 100°C	0 to +25%	+10 to +30%	ASTM F146
FUEL A 22 hours ambient temperatures	-5 to +10%	0 to +15%	ASTM F146
BS148 Transformer Oil 14 days at 90°C	+23.1%	+10%	ASTM F146



The company's products are used for a multiplicity of purposes and as the company has no control over the method of their applications or use, the company excludes all conditions or warranties, expressed or implied by statute or otherwise, as to their products and/or their fitness for any particular purpose. Any technical co-operation between the company and the customer is given for customers assistance only and without liability on the part of the company