



NEB120 NEOPRENE/EPDM FOAM RUBBER

MATERIAL SPECIFICATION SHEET

PROPERTIES	AVERAGE VALUE
ASTM D1056 (2000)	2C2
Density	110 - 130 kg m ³
Compression Deflection 25% (35-63)	40 kpa
Shore Hardness 00 / C Scale	40 / 15
Elongation – Minimum	> 200 %
Temperature Range	- 30°C / + 100°C
Water Absorption	< 3 % Vol
Tensile Strength	7.4 kg / cm ²
Flame Resistance	FMVSS302
	UL94 HF1**
	Self-Extinguishing
Environmental Protection	CFC & HCFC Free

The above figures are average values.

We recommend evaluation prior to use to ascertain the suitability of the material for the application.

** The material if tested will conform to UL94 HF1 although it is not listed by Underwriters Laboratories Inc.



The company's products are used for a multiplicity of purposes and as the company has no control over the method of their applications or use, the company excludes all conditions or warranties, expressed or implied by statute or otherwise, as to their products and/or their fitness for any particular purpose. Any technical co-operation between the company and the customer is given for customers assistance only and without liability on the part of the company