



RAM GASKET SOLUTIONS
GASKET ENGINEERING TECHNOLOGY

NEOPRENE INSERTION

MATERIAL SPECIFICATION SHEET

| PROPERTY | VALUE | UNIT |
|---------------------|------------------|-------------------|
| Elastomer | Neoprene | |
| Quality | Cotton Insertion | |
| Colour | Black | |
| Grade | C66 | |
| Hardness | 70° | Shore A |
| Specific Gravity | 1.4 | g/cm ² |
| Tensile Strength | 5 | MPa |
| Elongation at Break | 300 | % |
| Compression Set | 35 | % |
| Abrasion Resistance | 290 | mm ³ |
| Working Temperature | -20 to +110 | °C |

- Good strength and abrasion properties.
- Resists weathering and oxidative ageing.
- Resistant to some inorganic salts and acids and ozone.
- Flame retardant. Moderate resistance to petroleum based products other than aromatic and halogenated hydrocarbons.
- These are general properties, which will vary between grades.



ISO 9001:2015 Q93057 ISO 14001:2015 EMS 505718

The company's products are used for a multiplicity of purposes and as the company has no control over the method of their applications or use, the company excludes all conditions or warranties, expressed or implied by statute or otherwise, as to their products and/or their fitness for any particular purpose. Any technical co-operation between the company and the customer is given for customers assistance only and without liability on the part of the company