



NITRILE 70 O-RING CORD

MATERIAL SPECIFICATION SHEET

SPECIFICATION - ASTM D2000 M2BG710 B14 EA14 EO14 EO34	Test	Spec	ATSM Method
Original Properties			
Hardness, Shore A	73	70+/-5	D 2240
Tensile Strength, min, MPa	14.7	10	D 412
Elongation, min, %	350	250	D 412
Compression Set, Method B			D 2240
22 hrs at 100 deg c, max, %	13	25	
Water Resistance, 70 hrs at 100°C			D471
Hardness Change, points			
Volume Change, %			
IRM 901 Oil Resistance, 70 hrs at 100°C			D471
Hardness Change, points	+2	-5/+10	
Tensile strength change, %	+9	-25	
Elongation Change, max, %	-15	-45	
Volume Change, %	-3	-10/+5	
IRM 903 Oil Resistance, 70 hrs at 100°C			D471
Hardness Change, points	-10	-10/+5	
Tensile Change, max, %	-19	-45	
Elongation Change, max, %	-22	-45	
Volume change, %	+17	0/+25	
Specific Gravity	1.28	0/+0.05	
Colour: Black			



ISO 9001:2015 Q93057 ISO 14001:2015 EMS 505718

The company's products are used for a multiplicity of purposes and as the company has no control over the method of their applications or use, the company excludes all conditions or warranties, expressed or implied by statute or otherwise, as to their products and/or their fitness for any particular purpose. Any technical co-operation between the company and the customer is given for customers assistance only and without liability on the part of the company